

Refractory steel **SGS-R25-20**

The **SGS-R25-20 refractory steel** provides excellent resistance to oxidation thanks to its high chromium content. Due to its consistently good properties at high temperature, this steel meets a wide range of applications.



Designations

SEVA designation: **SGS-R25-20**

Standard designations :

AFNOR	Z 15 CNS 25-20 -M (NF A 32-057)
EN	X15CrNiSi25-21 (NF EN 10095)
DIN	1.4841
AISI	310



Chemical Analysis (en%)

Standardized (Standard NF A 32-057)

Fe	C	Mn	Si	Cr	Ni	P	S
Bal.	0.15	2	2	22 - 27	18 - 22	0.040	0.030



Mechanical properties

Hardness: 156 HB

Tensile test at room temperature:

Rp0,2 (MPa)	Rm (MPa)	A (%)
230	550	30

Hot tensile test:

Températures	300°C	600°C	750°C	900°C
Rp0,2 (en MPa)	460	370	100	60
Rm	NC	NC	190	70

Elastic modulus at 20°C: E = 195 GPa



Creep resistance

For casted products: breaking stress in N.mm⁻² (or MPa) for a duration of 10 000 hours:

700°C	800°C	900°C	1000°C
45	21	10	5



Applications

Areas of use

- Cement works
- Metallurgy
- Petrochemical industry
- Glass industry
- Hot forming toolings
- OGlass toolings

Maximum temperature of use

900°C

Types of parts produced

- Furnace equipment
- Moules de formage pour l'industrie verrière
- Moules pour le formage à chaud de tôles de titane destinées à l'industrie aéronautique (Hot Forming HF)



Standard structure

Austenitic with carbide precipitation.



Physical Properties

Density at 20 °C: 7,8

Expansion coefficient α en $10^{-6} K^{-1}$

Température	300°C	600°C
α	19,0	23,3



Other properties

Magnetism: Non-magnetic

Thermal conductivity at 20°C: 14 W.m⁻¹.K⁻¹

Thermal capacity at 20°C: 500 J.kg⁻¹.K⁻¹



Production

SEVA produces the **SGS-R25-20 alloy** in an electric induction furnace.

Cast in a sand mold.

Heat treatment: **Air hyperquenching**.



Compatible processes

	Compatibilité
Machining	● ● ● ● ●
Polishing	● ● ● ● ●
Welding	● ● ● ● ●
Forging	● ● ● ● ○

The information in this document is an average and not a guaranteed maximum or minimum value. The applications indicated for the grades described are for guidance only to assist the reader in his or her personal evaluation and are not warranties, expressed or implied, of suitability for any specific purpose. Saint-Gobain SEVA's liability shall in no case be extended to the choice of product or to the consequences of this choice.



www.saint-gobain-seva.com



Saint-Gobain SEVA

43 rue du Pont de Fer - BP 10176
71105 Chalon-sur-Saône cedex
France

Tél. : + 33 3 85 47 25 88
+ 33 3 85 47 28 06

at-seva@saint-gobain.com